

Rötzmeier Sicherheitsbehälter
Roetzmeier Safety Vessels

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics																fluoroplastics			elastomers			metals		COMMENT
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR	SI	AL	V2A	V4A	
Acetaldehyde	C ₂ H ₄ O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	Acetic aldehyde; Ethanal; Ethyl aldehyde
Acetaldehyde	C ₂ H ₄ O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Acetamide	C ₂ H ₅ NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	90 %	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1		
Acetic acid chloride	-> see: Acetyl chloride																													
Acetic acid sodium salt	-> see: Sodium acetate																													
Acetic aldehyde	-> see: Acetaldehyde																													
Acetic anhydride	C ₄ H ₆ O ₃	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1		
Acetic chloride	-> see: Acetyl chloride																													
Acetone	C ₃ H ₆ O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone
Acetonitrile	C ₂ H ₃ N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	Methyl cyanide; Cyanomethane; Ethanitrile
Acetyl chloride	-> see: Chloroacetone																													
Acetophenone	C ₈ H ₈ O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene
Acetyl chloride	C ₂ H ₃ ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	Acetic chloride; Ethanoyl chloride; Acetic acid chloride
Acetylene	C ₂ H ₂	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	Ethine; Ethyne
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																													
Acetylsalicylic acid	C ₉ H ₈ O ₄	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;
Acrylonitrile	C ₃ H _{3.5} N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/0	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide
Adipic acid	C ₆ H ₁₀ O ₄	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	1/0	(2)	(2)	Hexanedioic acid; Butanedicarboxylic acid, 1,4-
Alanine, L-	C ₃ H ₇ NO ₂	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	(0)	(2)	(2)	(2)	Aminopropanoic acid, L-2; aminopropanoic acid, alpha-
Allspice	—	—	ground	?		0/0	0/0	(2)	4/4	0/0	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	(2)	(2)	(0)	(1)	(1)	(1)	
Allyl acetate	C ₆ H ₁₀ O ₂	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	(1)	
Allyl alcohol	C ₃ H ₆ O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1		Vinyl carbinol; Propenyl alcohol
Allyl chloride	C ₃ H ₅ Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)		Chloro-1-propene, 3-; Chloropropylene, 3-
Allyl mustard oil	C ₈ H ₁₅ NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	0/0	0/0	0/0	4/4	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	(1)	oleum sinapis
Almond oil, sweet	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	(0)	(1)	1/1	1/1	
Alumina acidic	C ₂ H ₇ AlO ₅ x H ₂ O	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1	
Aluminium fluoride	AlF ₃	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	1/1	0/0	0/0	
Aluminum ammonium sulfate dodecahydrate	(NH ₄) ₂ Al(SO ₄) ₂	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3		
Aluminum chloride	AlCl ₃	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	0/0	0/0	1/0	1/0	1/1	2/2	1/1	1/1	1/0	1/0	1/0	1/0	0/0	4/4	4/4	3/4	
Aluminum chloride	AlCl ₃	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	0/0	4/4	4/4	3/4			
Aluminum chloride	AlCl ₃	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/1	(2)	1/0	1/0	0/0	4/4	4/4	3/4		
Aluminum hydroxide	Al(OH) ₃	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Aluminum nitrate	Al(NO ₃) ₃	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0		
Aluminum oxide, alpha-	Al ₂ O ₃	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	
Aluminum sodium sulfate	NaAl(SO ₄) ₂	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	1/1	0/0	1/0	1/2	1/1	
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2		
Aminic acid	-> see: Formic acid																													
Aminoacetic acid	-> see: Glycine																													
Aminoethanol	C ₂ H ₇ NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Aminopropanoic acid, alpha	-> see: Alanine, L-																													
Ammonium acetate	C ₂ H ₇ NO ₂	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1											

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics			elastomers			metals		COMMENT			
						HDPE	LDPE	PA	PC	PETG	PMMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	AL		V2A	V4A	
Ammonium chloride	(NH ₄)Cl	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	sal ammoniac
Ammonium difluoride	F ₂ H ₂ N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammonium ferric sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammonium ferrous sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	0/0	(4)	0/0	(4)	(1)	(1)			
Ammonium fluoride	(NH ₄)F	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	1/0	0/0	0/0	1/0	0/0	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)			
Ammonium fluoride	(NH ₄)F	012125-01-8	aqueous	T, C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3			
Ammonium glycolate	C ₂ H ₃ NO ₃	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)	Acetic acid	
Ammonium heptamolybdate	(NH ₄) ₆ Mo ₇ O ₂₄	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)			
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1		
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1		
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1		
Ammonium mercaptan	-> see: Ammonium bisulfide																														
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	Nitric acid; Ammonium salt	
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1		
Ammonium nitrite	(NH ₄)NO ₂	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)			
Ammonium oxalate	C ₂ H ₈ N ₂ O ₄	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1		
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	(3)	4/4	0/0	4/4	(4)	3/4				
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4			
Ammonium phosphate, Mono-	(NH ₄)H ₂ PO ₄	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)			
Ammonium polyphosphate (APP)	(NH ₄ PO ₃) _n	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)	
Ammonium rhodanide	-> see: Ammonium thiocyanate																														
Ammonium salt	-> see: Ammonium nitrate																														
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2		
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	Diammonium sulfide;		
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)		
Ammonium sulfocyanide	-> see: Ammonium thiocyanate																														
Ammonium thiocyanate	CH ₃ N ₂ S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)	Ammonium sulfocyanide; Ammonium rhodanide; Thiocyanic acid, Ammonium salt; Ammonium sulfocyanate	
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Amyl acetate, normal	C ₇ H ₁₁ O ₂	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	
Amyl alcohol, n-	-> see: Pentanol, 1-																														
Amyl chloride	C ₅ H ₁₁ Cl	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L		
Amyl cinnamic aldehyde	C ₁₂ H ₁₆ O	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)	odoriferous substance	
Aniline	C ₆ H ₇ N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0		
Aniline hydrochloride	C ₆ H ₇ ClN	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4			
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Anisole	C ₇ H ₈ O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	(1)		
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	glycol-water-mixture	
Antimony pentachloride	SbCl ₅	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)			
Antimony trichloride	SbCl ₃	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4			
Antimony trichloride	SbCl ₃	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4			
Antimony trichloride	SbCl ₃	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4			
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(2)	(1)	(1)	(1)			
Arsenic acid	H ₃ AsO ₄	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1		
Arsenic acid	H ₃ AsO ₄	022538-92-7		T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1		
Arsenic pentoxide	As ₂ O ₅	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)			
Ascorbic acid	C ₆ H ₈ O ₆	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1																					

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics			elastomers			metals		COMMENT				
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR	SI		AL	V2A	V4A	
Barium chloride	BaCl ₂	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/2L	1/1L
Barium chloride	BaCl ₂	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/2L	1/1L
Barium dibromide	BaBr ₂	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Barium hydroxide	Ba(OH) ₂	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1			
Barium hydroxide	Ba(OH) ₂	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1			
Barium sulfide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)		
Battery acid	H ₂ SO ₄	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3		Sulfuric acid;	
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1			
Beef tallow emulsion	—	—	sulfonated	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)		
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)			
Benzaldehyde	C ₇ H ₆ O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		artificial almond oil
Benzene	C ₆ H ₆	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1		Cyclohexatriene; Benzol
Benzene chloride	-> see: Chlorobenzene																														
Benzenesulfonic acid	C ₆ H ₅ SO ₃	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0		
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1		
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1		
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoyl chloride	C ₇ H ₅ ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)		Benzenecarbonyl chloride; Benzoic acid chloride	
Benzyl acetate	C ₉ H ₁₀ O ₂	000140-11-4		Xn, Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl alcohol	C ₇ H ₈ O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl benzoate	C ₁₄ H ₁₂ O ₂	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)			
Benzyl chloride	C ₇ H ₇ Cl	000100-44-7	100 %	T, Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L			
Benzyl ether	C ₁₄ H ₁₄ O	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)			
Bismuth chloride	BiCl ₃	007787-60-2		Xi		1/1	1/1	(3)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0				
Bismuth nitrate, basic	Bi ₂ O(HO) ₂ (NO ₃) ₄	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0				
Bisulfite solution	NaHSO ₃	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1				
Bisulfite solution, containing SO ₂	NaHSO ₃	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	1/3	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1				
Bitter almond oil	C ₇ H ₆ O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		mainly: benzaldehyde
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)			
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Boric acid	H ₃ BO ₃	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1		
Boric acid	H ₃ BO ₃	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1		
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromic acid	HBrO ₃	007789-31-3	concentrated	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)			
Bromine	Br ₂	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4		
Bromine pentafluoride	BrF ₅	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)				
Bromine steams	Br ₂	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)			
Bromine trifluoride	BrF ₃	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)				
Bromine water	Br ₂ +H ₂ O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4			
Bromobenzene	C ₆ H ₅ Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromochloromethane	CH ₂ BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0			
Bromotrifluoromethane	CBBrF ₃	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	4/4	0/0	(3)	0/0	0/0			
Butadiene, 1,3-	C ₄ H ₆	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Butanal	-> see: Butyraldehyde																														
Butane	C ₄ H ₁₀	000106-97-8	techn. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Butanedicarboxylic acid, 1,4-	-> see: Adipic acid																														
Butanetriol	C ₄ H ₁₀ O ₃	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		isomer not indicated in the source
Butanol	-> see: Butyl alcohol, normal																														
Butene	C ₄ H ₈	—	techn. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)		isomer not indicated in the source	
Butoxybutane, 1-	-> see: Butyl ether, (Di-) n-																														
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0														

Rötzmeier Sicherheitsbehälter
Roetzmeier Safety Vessels

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	thermoplastics																fluoroplastics		elastomers		metals		COMMENT		
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR	SI	AL		V2A	V4A
Butyl alcohol, normal	C ₄ H ₁₀ O	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	Propyl carbinol; Butanol
Butyl alcohol, sec-	C ₄ H ₁₀ O	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	Butanol, -2; Methyl ethyl carbinol; Butylene hydrate
Butyl alcohol, tert-	C ₄ H ₁₀ O	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	
Butyl aldehyde	-> see: Butyraldehyde																													
Butyl carbinol, n-	-> see: Pentanol, 1-																													
Butyl ether, (Di-) n-	C ₈ H ₁₈ O	000142-96-1	techn. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	Butoxybutane, 1-;
Butyl ethylene	-> see: Hexene, 1-																													
Butyl stearate	C ₂₂ H ₄₄ O ₂	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	
Butylamine	C ₄ H ₁₁ N	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Butylene glycol	C ₄ H ₁₀ O ₂	—	techn. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	isomer not indicated in the source
Butylene hydrate	-> see: Butyl alcohol, sec-																													
Butylphenol	C ₁₀ H ₁₄ O	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	isomer not indicated in the source
Butylphenol, p-tert	C ₁₁ H ₁₅ NO	000098-54-4	techn. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	
Butyraldehyde	C ₄ H ₈ O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	Butanal; Butyl aldehyde
Butyric acid	C ₄ H ₈ O ₂	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0	
Calcium bicarbonate	Ca(HCO ₃) ₂	—	saturated	—		1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	(1)	0/0	(2)	(1)	(1)	
Calcium bisulfite	Ca(HSO ₃) ₂	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	
Calcium bisulfite	Ca(HSO ₃) ₂	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	
Calcium bromide	CaBr ₂	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	
Calcium carbide	CaC ₂	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	carbide, reacts with water to acetylene - highly flammable!
Calcium carbonate	CaCO ₃	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Calcium chlorate	Ca(ClO ₃) ₂	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	
Calcium chloride	CaCl ₂	010043-52-4	alkoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	
Calcium chloride	CaCl ₂	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/3	1/2L	1/2L	
Calcium hydroxyde	CaH ₂ O ₂	001305-62-0	aqueous (Xi)			1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	
Calcium hydroxyde	CaH ₂ O ₂	001305-62-0	concentrated	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	
Calcium hypochlorite	Ca(OCl) ₂	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	bleaching powder
Calcium hypochlorite	Ca(OCl) ₂	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	2/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/3	4/4	0/0	4/4	3/0	2/0	bleaching powder	
Calcium nitrate	Ca(NO ₃) ₂	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	
Calcium nitrate	Ca(NO ₃) ₂	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	
Calcium oxide	CaO	001305-78-8	powder	C		1/0	1/1	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	0/0	(3)	1/1	1/1		
Calcium phosphate	Ca ₃ (PO ₄) ₂	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Calcium phosphate	Ca ₃ (PO ₄) ₂	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected
Calcium sulfate	CaSO ₄	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	plaster
Calcium sulfide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	
Calcium sulfide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	
Calciumacetat	C ₄ H ₆ CaO ₄	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	
Camphor	C ₁₀ H ₁₆ O	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	from cinnomum camphora
Caprylic alcohol	C ₈ H ₁₈ O	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Caraway	—	—	ground	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)	
Carbazole	C ₁₂ H ₉ N	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)		
Carbolineum	—	008001-58-9	aqueous (Xn)			1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	1/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	Creosote;
Carbon dioxide	CO ₂	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1		
Carbon dioxide, damp	CO ₂	000124-38-9	techn. pure																											

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics		elastomers		metals		COMMENT				
						HDPE	LDPE	PA	PC	PETG	PMMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR		SI	AL	V2A	V4A
Diphenyl ether	C ₁₂ H ₁₀ O	000101-84-8		Xn/Xi	0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		
Diphenylamine	C ₁₂ H ₁₁ N	000122-39-4		T	0/0	0/0	0/0	(3)	(0)	0/0	(2)	(3)	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)			
Diphyl	—	008004-13-5		?	0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	mixture with diphenyl and diphenyl ether; Bayer		
Dipropyl ketone	C ₇ H ₁₄ O	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)			
Dipropylene glycol	C ₆ H ₁₄ O ₃	025265-71-8		Xi	0/0	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	(1)	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropylene glycol (mono)methyl ether	C ₆ H ₁₀ O ₂	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	isomer not indicated in the source	
Disodium phosphate	Na ₂ HPO ₄	007558-79-4		(Xi)	1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1			
Dispersion of rubber	—	—		?	0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)	(1)	latex		
Dithionous acid, disodium salt	-> see: Sodium hydrosulfite																													
Divinylene oxide	-> see: Furan																													
Dope, viscous ~	—	—		(Xn, Xi)	1/1	1/1	4/4	(3)	0/0	0/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4			
Emulsifiers	—	—		?	0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K			
Emulsions for fotos	—	—		?	1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0			
Ephetin	—	—	10% in water	?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Epichlorhydrin	C ₃ H ₅ ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0		
Epoxypropane, 1,2-	-> see: Propylene oxid																													
Ethanal	-> see: Acetaldehyde																													
Ethanedioic acid	-> see: Oxalic acid																													
Ethanenitrile	-> see: Acetonitrile																													
Ethanoyl chloride	-> see: Acetyl chloride																													
Ethoxybenzene	C ₈ H ₁₀ O	000103-73-1		?	0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Ethyl phenyl ether; Phenyl ethyl ether; Phenetole		
Ethyl acetate	C ₄ H ₈ O ₂	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)		
Ethyl acrylate	C ₅ H ₈ O ₂	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/0	1/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	1/1	1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	1/1		
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		
Ethyl aldehyde	-> see: Acetaldehyde																													
Ethyl benzoate	C ₉ H ₁₀ O ₂	000093-89-0		Xn	2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethyl butyrate	C ₈ H ₁₆ O ₂	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl chloride	-> see: Monochloroethane																													
Ethyl chloroacetate	C ₄ H ₇ ClO ₂	000105-39-5	techn. pure	T/Xi	1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0		
Ethyl cyanoacetate	C ₃ H ₇ NO ₂	000105-56-6		Xn/Xi	1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)		
Ethyl formate	C ₃ H ₆ O ₂	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl lactate	C ₅ H ₁₀ O ₃	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl mercaptan	C ₂ H ₆ S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethyl phenyl ether	-> see: Ethoxybenzene																													
Ethyl silicate	C ₈ H ₂₀ SiO ₄	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Ethylbenzene	C ₈ H ₁₀	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)		
Ethylene	C ₂ H ₄	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)		
Ethylene dibromiden (EDB)	C ₂ H ₄ Br ₂	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	Dibromoethane, 1,2-;	
Ethylene glycol	C ₂ H ₆ O ₂	000107-21-1		Xn	1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		
Ethylene glycol monobutyl ether	C ₈ H ₁₆ O ₂	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)		
Ethylene glycol monoethyl ether	C ₄ H ₁₀ O ₂	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monoethyl ether acetate	C ₆ H ₁₂ O ₃	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)		
Ethylene glycol monomethyl ether	C ₃ H ₈ O ₂	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monomethyl ether oleate	C ₂₁ H ₄₀ O ₃	000111-10-4		?	1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)	Kapsolat; Methoxyethyl oleate; Methyl cellosolveoleate; plasticiser	
Ethylene oxide	C ₂ H ₄ O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	(1)	(1)		
Ethylendiaminetetraacetic acid (EDTA)	C ₁₀ H ₁₆ N ₂ O ₈	000060-00-4		Xi	1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	
Ethylhexanol-1	C ₈ H ₁₈ O	000104-76-7		Xn/Xi	0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		
Ethyne	-> see: Acetylene																													
Eucalyptus oil	—	008000-48-8		?	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Exhaust gases, alkaline	—	—		?	1/1	0/0	(2)	0/0	0/0	(0)	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)			
Exhaust gases, containing carbon dioxide	—	—	small	?	1/1	0/0	(1)	(1)	(1)	(1)	1/1																			

Rötzmeier Sicherheitsbehälter
Roetzmeier Safety Vessels

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics																	fluoroplastics		elastomers		metals		COMMENT	
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR	SI	AL	V2A		V4A
Exhaust gases, containing hydrogen fluoride	—	—	small	?	1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)			
Exhaust gases, containing nitrose	—	—	small	?	1/1	0/0	(3)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)				
Exhaust gases, containing sulfur dioxide	—	—	small	?	1/1	0/0	(2)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1				
Exhaust gases, containing sulfur trioxide	—	—	small	?	1/1	0/0	(4)	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)			
Exhaust gases, containing sulfuric acid	—	—	each	?	1/1	0/0	(4)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)				
Fat, animal	—	—	—	—	0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1			
Fat, mineral	—	—	—	(—)	0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1			
Fat, vegetable	—	—	—	—	0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1			
Fats, edible oil	—	—	—	—	0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1			
Fatty alcohol sulfonates	—	—	aqueous	(Xn, Xi)	1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	detergents		
Ferric chloride	FeCl ₃	007705-08-0	saturated	Xn	1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4			
Ferric nitrate	Fe(NO ₃) ₃	010421-48-4	aqueous	(O, Xn)	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1			
Ferric nitrate	Fe(NO ₃) ₃	010421-48-4	saturated	O, Xn	1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1			
Ferric sulfate	Fe ₂ (SO ₄) ₃	010028-22-5	saturated	Xi	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1			
Ferrous chloride	FeCl ₂	007758-94-3	saturated	Xn	1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1			
Ferrous sulfate	FeSO ₄	007720-78-7	saturated	(Xn)	1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1			
Ferrous sulfate	FeSO ₄	007720-78-7	aqueous	(Xn)	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1			
Ferrous sulfate	FeSO ₄	007720-78-7	—	Xn	1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1			
Fire-damp	—	—	—	F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane	
Fixer for fotos	—	—	—	?	?	1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/0	1/0	0/0	(2)	1/0	1/0			
Fluid 101, 100 °C	—	—	—	?	?	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0	Brake fluid, based on polyglycoles	
Fluorides	—	—	—	T	1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluorine	F ₂	007782-41-4	—	O, T+, C+	4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/3	1/2	1/2	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)		
Fluorobenzene	C ₆ H ₅ F	000462-06-6	—	F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0			
Fluorocarbons	—	—	—	?	0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0	resistance depends on type	
Formaldehyde solution	CH ₂ O	000050-00-0	10 %	Xn	1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1			
Formaldehyde solution	CH ₂ O	000050-00-0	30 %	T	1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1		
Formaldehyde solution	CH ₂ O	000050-00-0	40 %	T	1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1			
Formamide	CH ₃ NO	000075-12-7	techn. pure	T/Xi	1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	1/0	1/1	(3)	3/0	273	4/4	0/0	1/1	1/1	1/1			
Formic acid	CH ₂ O ₂	000064-18-6	50 %	C	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	Hydrogen carboxylic acid; Methanoic acid; Aminic acid; Formylic acid	
Formic acid	CH ₂ O ₂	000064-18-6	98-100 %	C	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2		
Formic acid	CH ₂ O ₂	000064-18-6	3 %	Xi	1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1		
Freon 11	-> see: Trichlorofluoromethane																													
Freon 11	-> see: Trichlorofluoromethane																													
Freon 112	-> see: Tetrachlorodifluoroethane																													
Freon 112	-> see: Tetrachlorodifluoroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoroethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 14	-> see: Carbon tetrafluoride																													
Freon 14	-> see: Carbon tetrafluoride																													
Freon 142b	-> see: Chlorodifluoroethane																													
Freon 142b	-> see: Chlorodifluoroethane																													

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	--- fluoroplastics ---		-- elastomers --		-- metals --		COMMENT					
																				PTFE	PVDF	EPDM	FPM	NBR	SI		AL	V2A	V4A		
Freon 152a	-> see: Difluoroethane																														
Freon 152a	-> see: Difluoroethane																														
Freon 21	-> see: Dichlorodifluoromethane																														
Freon 21	-> see: Dichlorodifluoromethane																														
Freon 218	-> see: Octafluoropropane																														
Freon 218	-> see: Octafluoropropane																														
Freon 22	-> see: Chlorodifluoromethane																														
Freon 22	-> see: Chlorodifluoromethane																														
Freon 31	-> see: Chlorofluoromethane																														
Freon 31	-> see: Chlorofluoromethane																														
Freon 32	-> see: Difluoromethane																														
Freon 32	-> see: Difluoromethane																														
Freon C 318	-> see: Perfluorocyclobutane																														
Freon C 318	-> see: Perfluorocyclobutane																														
Freon C316	-> see: Dichlorohexafluorocyclobutane																														
Freon C316	-> see: Dichlorohexafluorocyclobutane																														
Frigen 12	-> see: Dichlorodifluoromethane																														
Frigen 12	-> see: Dichlorodifluoromethane																														
Frigen 21	-> see: Dichlorodifluoromethane																														
Frigen 21	-> see: Dichlorodifluoromethane																														
Frigen 22	-> see: Chlorodifluoromethane																														
Frigen 22	-> see: Chlorodifluoromethane																														
Fructose	C ₆ H ₁₂ O ₆	000057-48-7	each	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1		
Fruit pulp	—	—	—	—	1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1		
Fruit wine	—	—	—	—	1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1		
Fuel + 20% ethyl alcohol	—	—	—	F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Fuel + 20% methyl alcohol	—	—	—	F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Fuel, Normal	—	—	—	F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Fuel, piston engine (JP)	—	—	—	(Xn)	0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	(1)		
Fuel, Super	—	—	—	F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Furalmethanal, 2-	-> see: Furfural																														
Furan	C ₄ H ₄ O	000110-00-9	—	F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Furfuran; Divinylene oxide; Oxacyclopentadiene	
Furancarboxyaldehyde, 2-	-> see: Furfural																														
Furfural	C ₅ H ₄ O ₂	000098-01-1	—	T	1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	Furancarboxyaldehyde, 2-; Furaldehyde, 2-; Furalmethanal, 2-
Furfuryl alcohol	C ₅ H ₆ O ₂	000098-00-0	techn. pure	Xn	1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	(1)		
Gallic acid	C ₇ H ₆ O ₅ x H ₂ O	000149-91-7	—	Xi	1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1		
Gas liquor	—	—	—	?	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0	0/0		
Gas oil	—	—	—	(Xn)	0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)	(1)		
Gas, natural	—	—	—	F+	X	0/0	0/0	0/1/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	(1)	mainly methane	
Gasoline	—	008006-61-9	—	(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)	(1)		
Gasoline	C ₈ H ₁₂ - C ₁₂ H ₂₆	086290-81-5	—	F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	fuel, lead-free	
Gearbox oil, EP (Hypoid), 110°C	—	—	—	?	0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1	1		
Gelatin	—	009000-70-8	each	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1		
Genantlin	—	—	—	Xn	0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; Clariant	
Ginger	—	—	ground	?	0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	(1)		
Glucose	C ₆ H ₁₂ O ₆	000050-99-7	each	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glue (bone glue)	—	—	each	—	1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	1/1		
Glycerol	C ₃ H ₈ O ₃	000056-81-5	each	Xi	1/1	1/1	1/0	3/3	1/0	1/0	1/1	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	Glycerin; Propanetriol, 1,2,3-; Trihydroxypropane, 1,2,3-	
Glycine	C ₂ H ₅ NO ₂	000056-40-6	10 %	—	1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	(2)	Glyccol; Aminoacetic acid	
Glycolic acid	C ₂ H ₄ O ₃	000079-14-1	37 %	Xn	1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/3		
Glycolic acid	C ₂ H ₄ O ₃	000079-14-1	70 %	C, Xn	1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/3		
Glysantin	—	—	—	Xn	1/1	1/1	3/3	(2)	1/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	antifreeze agent , based on glycol; BASF		
Gum tragacanth	—	009000-65-1	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1		
HD-Oil motor oil, without aromatics	—	—	—	?	1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1	1/1		

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	thermoplastics														fluoroplastics				elastomers		metals		COMMENT						
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR	SI	AL		V2A	V4A				
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1	
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	0/0	(1)	0/0	(1)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1	1/1	cleaner
Heptane, normal	C ₇ H ₁₆	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1		
Heptanol, 1-	C ₇ H ₁₆ O	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)	
Heptanone	C ₇ H ₁₄ O	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)	isomer not indicated in the source	
Hexachlorbenzene (HCB)	C ₆ Cl ₆	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0	
Hexachlorcyclohexane (alpha-BHC)	C ₆ H ₆ Cl ₆	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0	
Hexahydropyridine	—	—		-> see: Piperidine																														
Hexaldehyde, n-	C ₆ H ₁₂ O	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Hexamethylenetetramine	C ₆ H ₁₂ N ₄	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	Methanamine; Hexamine; Urotropin
Hexane, n-	C ₆ H ₁₄	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	
Hexanedioic acid	—	—		-> see: Adipic acid																														
Hexanetriol	C ₆ H ₁₄ O ₃	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	1/0	0/0	(1)	(1)	(1)	(1)	(1)	isomer not indicated in the source	
Hexene, 1-	C ₆ H ₁₂	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	Butyl ethylene; Hexylene
Hexyl alcohol	C ₆ H ₁₄ O	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)					
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)		
Hydraulic fluids, HFA	—	—	50 °C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50 °C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60 °C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0			
Hydraulic fluids, HFD-R	—	—	100 °C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100 °C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oil (based on mineral oil)	—	—	?	?		0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1			
Hydrazine	N ₂ H ₄	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	Diamide; Diamine; Nitrogen hydride	
Hydrazine hydrate	N ₂ H ₆ O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3			
Hydrocyanic acid, sodium salt	—	—		-> see: Sodium cyanide																														
Hydrogen	H ₂	001333-74-0	techn. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1		
Hydrogen bromide	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)					
Hydrogen bromide	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)					
Hydrogen bromide	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/1	4/4	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)					
Hydrogen carboxylic acid	—	—		-> see: Formic acid																														
Hydrogen chloride	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4			
Hydrogen chloride	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4			
Hydrogen chloride	HCl	007647-01-0	concentrated	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4				
Hydrogen chloride	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	4/4	4/4	salt acid	
Hydrogen chloride (gas)	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L					
Hydrogen cyanide	HCN	000074-90-8	techn. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	1/0			
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0					
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)					
Hydrogen fluoride	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	2/3	2/0	0/0	1/1	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0			
Hydrogen fluoride	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4				
Hydrogen fluoride	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	0/0	4/4	4/4	4/4				
Hydrogen fluoride	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	0/0	4/4	(2)	0/0																					

Rötzmeier Sicherheitsbehälter
Roetzmeier Safety Vessels

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	--- fluoroplastics ---		-- elastomers --		-- metals --		COMMENT				
																					PTFE	PVDF	EPDM	FKM	NBR	SI		AL	V2A	V4A	
Isobutyl acetate	C ₈ H ₁₂ O ₂	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/0	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	Methylpropyl acetate, 2-; Methylpropyl ethanoate, Beta-	
Isobutyl alcohol	-> see: Isobutanol																														
Isobutyltrimethylmethane	-> see: Trimethylpentane, 2,2,4-																														
ISO-Fluid			liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1		
ISO-Fluid A				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)		
ISO-Fluid B				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
ISO-Fluid C				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
ISO-Fluid D				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)		
Iso-octane	-> see: Trimethylpentane, 2,2,4-																														
Isopropyl acetate	C ₈ H ₁₆ O ₂	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isopropyl alcohol	C ₃ H ₈ O	000067-63-0	techn. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	1/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)		
Isopropyl carbinol	-> see: Isobutanol																														
Isopropyl chloride	C ₃ H ₇ Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Jan						1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1		
Juices						1/1	1/1	1/0	1/0	1/0	1/1	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1		
Kapsolat	-> see: Ethylene glycol monomethyl ether oleate																														
Kerosene		008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	lamp oil	
Kerosene			techn. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1		
Lactames				?		0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)	cyclic amides		
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	lactol		
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	3/4	1/1	1/4	0/0	1/0	1/3	1/2	lactol		
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	3/4	1/1	1/4	0/0	1/0	1/3	1/2	lactol		
Lactose	C ₁₂ H ₂₂ O ₁₁	000063-42-3	aqueous			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1		
Lanolin		008006-54-0	techn. pure			3/3	3/3	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1			
Lard						0/0	0/0	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		
Latex				?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	dispersion of rubber		
Laurel			ground	?		0/0	0/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)			
Lauryl alcohol	C ₁₂ H ₂₆ O	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Lauryl chloride	C ₁₂ H ₂₅ Cl	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavender oil		008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Lead acetate	C ₄ H ₈ PbO ₄	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1			
Lead acetate	C ₄ H ₈ PbO ₄	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1		
Lead nitrate	Pb(NO ₃) ₂	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0		
Lead nitrate	Pb(NO ₃) ₂	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0		
Lead stearate	C ₃₆ H ₇₀ PbO ₄	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	small solubility - no chemical effect expected	
Lead sulfate	PbSO ₄	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	small solubility - no chemical effect expected	
Lead tetraethyl (TEL)	C ₈ H ₁₈ Pb	000078-00-2	techn. pure	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)		
Lemon juice						1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1		
Lemon oil		084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)	mainly limonene	
Lemongrass oil		008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Ligroin		008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	4/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	petroleum ether	
Lime chloride	[3 x CaCl(OCl) + C ₂]		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	chloride of lime, bleach	
Lime chloride	[3 x CaCl(OCl) + C ₂]			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	chloride of lime, bleach
Limonene, DL-	C ₁₀ H ₁₆	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1			
Linseed oil		008001-26-1	techn. pure			1/1	1/3	1/0	1/0	1/0	1/1	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Liqueurs						1/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Lube oils				?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1				

CHEMICALS	FORMULA	CAS-NR.	CONCENTRAT ION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT													
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE	PVDF	EPDM	FKM		NBR	SI	AL	V2A	V4A								
Nickel dichloride	NiCl ₂	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L										
Nickel dichloride	NiCl ₂	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L									
Nickel sulfate	NiSO ₄	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1									
Nickel sulfate	NiSO ₄	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1									
Nickelous nitrate	Ni(NO ₃) ₂	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0									
Nicotine	C ₁₀ H ₁₄ N ₂	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)									
Nicotinic acid	C ₆ H ₇ NO ₂	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0									
Nitric acid	HNO ₃	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1									
Nitric acid	HNO ₃	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2									
Nitric acid	HNO ₃	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2									
Nitric acid	HNO ₃	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	3/3									
Nitric acid	HNO ₃	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2									
Nitric acid																																						
Nitric acid, magnesium salt																																						
Nitric acid, potassium salt																																						
Nitro benzoic acid	C ₇ H ₅ NO ₄	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	isomer not indicated in the source		
Nitro reducer	—	—		?	X	0/0	0/0	3/0	4/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	solvent cleaner mixture	
Nitrobenzene	C ₆ H ₅ NO ₂	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/1	1/1	1/1									
Nitroethane	C ₂ H ₅ NO ₂	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0			
Nitrogen	N ₂	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1	1/1									
Nitrogen hydride																																						
Nitrogen tetroxide	N ₂ O ₄	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Nitroglycerine	C ₃ H ₅ (NO ₃) ₃	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	1/0	0/0	0/0	3/0	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Nitrohydrochloric acid	HNO ₃ + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4										
Nitropropane	C ₃ H ₇ NO ₂	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	isomer not indicated in the source	
Nitrose gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)									
Nitrotoluene	C ₇ H ₇ NO ₂	001321-12-6	techn. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	nitrogen monoxide + nitrogen dioxide	
Nitrous acid, sodium salt																																						
Nitrous oxide	N ₂ O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	nitric oxide	
Nonanol																																						
Nonyl alcohol	C ₉ H ₂₀ O	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)										
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)										
Octafluoropropane	C ₃ F ₈	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Octane	C ₈ H ₁₈	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1									
Octyl carbinol																																						
Octyl cresol ?	C ₁₅ H ₂₄ O	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	isomer not indicated in the source	
Oils and fats, vegetable	—	—		?		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1									
Oils, essential	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)									
Oleic acid	C ₁₈ H ₃₄ O ₂	000112-80-1	techn. pure	Xi		1/3	1/3	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1										
Oleic acid methyl ester	C ₁₉ H ₃₆ O ₂	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(4)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)									
Oleum	H ₂ SO ₄ x SO ₃	008014-95-7	10 % SO ₃	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1									
Oleum steams	—	—	small	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)									
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1									
Orange juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	(1)	(1)									
Orange oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)									
Orange oil, bitter	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4																								

CHEMICALS	FORMULA	CAS-NR.	CONCENTRAT ION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM		NBR	SI	AL	V2A	V4A
Pyrogallic acid	C ₆ H ₆ O ₃	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	0/0	1/1	1/1	1/1			
Pyrolineous oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)			
Pyrrrole	C ₄ H ₅ N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	Azole; Imidole		
Quinine	C ₂₀ H ₂₄ N ₂ O ₂	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	0/0	(2)	(1)	(1)			
Quinol	-> see: Hydroquinone																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	for moisture-proofing of textiles; BASF	
Resorcinol	C ₆ H ₆ O ₂	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0	
Resorcinol	C ₆ H ₆ O ₂	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Roaster off-gas	—	—	each	(T)		0/0	0/0	(2)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)	
Rum ether	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)	disinfectant; Schülke & Mayr	
Salicyl acid	C ₇ H ₆ O ₃	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	1/0	3/0	0/0	1/0	1/0	
Salicyl acid	C ₇ H ₆ O ₃	000069-72-7	powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/2	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	
Salicylaldehyde	C ₇ H ₆ O ₂	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)	
Salt spring	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	1/0	1/1	0/0	3/4	1/3	1/2
Salt water, sea water	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	
Saltpeter	-> see: Potassium nitrate																													
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1	
Sea water	—	—		—		1/1	1/1	1/0	1/1	0/0	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L		
Silicofluoric acid	H ₂ SiF ₆	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	
Silicone greases	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1	
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	polysiloxane
Silver acetate	C ₂ H ₃ AgO ₂	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0		
Silver nitrate	AgNO ₃	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	lunar caustic	
Silver nitrate	AgNO ₃	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	lunar caustic	
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	(1)	(1)	based on phosphoric ester; Solutia	
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	(1)	(1)	based on phosphoric ester; Solutia	
Soaps, liquid	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Soapy solution	—	—	each	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	
Sodium acetate	C ₂ H ₃ NaO ₂	000127-09-3	each	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	2/2	1/1	2/2	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	Acetic acid sodium salt;	
Sodium benzoate	C ₇ H ₅ NaO ₂	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	
Sodium benzoate	C ₇ H ₅ NaO ₂	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	
Sodium benzoate	C ₇ H ₅ NaO ₂	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	
Sodium bicarbonate	NaHCO ₃	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	
Sodium bisulfate	NaHSO ₄	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	
Sodium bisulfate	NaHSO ₄	007681-38-1	each	(C)		1/1	1/1	1/0	1/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	
Sodium bisulfite	NaHSO ₃	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/1	1/1	
Sodium borate	Na ₂ B ₄ O ₇ x 10 H ₂ O	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	
Sodium borate	Na ₂ B ₄ O ₇ x 10 H ₂ O	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	
Sodium bromate	NaBrO ₃	007789-38-0	each	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	
Sodium bromide	NaBr	007647-15-6	each	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	
Sodium carbonate	Na ₂ CO ₃	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	
Sodium carbonate	Na ₂ CO ₃	000497-19-8	aqueous	Xi		1																								

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT						
						HDPE	LDPE	PA	PC	PETG	PMMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE	PVDF	EPDM	FKM		NBR	SI	AL	V2A	V4A	
Sodium hydroxide	NaHO	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaHO	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye
Sodium hydroxide	NaHO	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaHO	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	caustic soda, sodium hydrate, soda lye
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	12.5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	sodium oxychloride, sodium chloride oxide		
Sodium iodide	NaI	007681-82-5	each	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/3	(1)	1/1	0/0	1/1	3/4	3/4		
Sodium metabisulfite	Na ₂ S ₂ O ₅	007681-57-4	each	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Sodium nitrate	NaNO ₃	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	chile saltpeter	
Sodium nitrate	NaNO ₃	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	chile saltpeter	
Sodium nitrite	NaNO ₂	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	Nitrous acid, sodium salt;	
Sodium nitrite	NaNO ₂	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1		
Sodium oxalate	C ₂ Na ₂ O ₄	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Sodium perborate	NaBO ₂ (HO) ₂ x 3H ₂ O	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perborate	NaBO ₂ (HO) ₂ x 3H ₂ O	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perchlorate	NaClO ₄	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1		
Sodium peroxide	Na ₂ O ₂	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1		
Sodium peroxide	Na ₂ O ₂	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)		
Sodium persulfate	Na ₂ S ₂ O ₈	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0		
Sodium phosphate	Na ₃ PO ₄ x 12H ₂ O	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1		
Sodium phosphate	Na ₃ PO ₄ x 12H ₂ O	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1		
Sodium polyphosphates	(NaPO ₃) ₆	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0	0/0		
Sodium silicate	Na ₂ Si ₂ O ₇	001344-09-8	each	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Sodium silicate	Na ₂ Si ₂ O ₇	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	1/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/1	waterglass	
Sodium stearate	C ₁₈ H ₃₅ NaO ₂	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Sodium sulfate	Na ₂ SO ₄	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1		
Sodium sulfate	Na ₂ SO ₄	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1		
Sodium sulfate	Na ₂ SO ₄	007757-82-6	—	—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	
Sodium sulfide	Na ₂ S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)		
Sodium sulfide	Na ₂ S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2		
Sodium sulfite	Na ₂ SO ₃	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	Sulfurous acid, disodium salt;	
Sodium sulfoxylate	—	—	—	—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	-> see: Sodium hydrosulfite	
Sodium thiosulfate	Na ₂ S ₂ O ₃ x 5H ₂ O	010102-17-7	each	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"	
Sodium thiosulfate	Na ₂ S ₂ O ₃ x 5H ₂ O	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	1/3	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"	
Sodium thiosulfate	Na ₂ S ₂ O ₃ x 5H ₂ O	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	fixer natron, "sodium hyposulfite"	
Soft soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)			
Soya oil	—	008001-22-7	—	—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1			
Spermaceti	—	008002-23-1	—	—		0/0	1/3	(1)	1/1	1/0	0/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Spindle oil	—	—	?	?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1			
Spinning bath acid	—	—	100mg CS ₂ /l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4		
Spirit (of wine)	C ₂ H ₆ O	—	—	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	ethyl alcohol	
Spirits	C ₂ H ₆ O	—	—	—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	ethyl alcohol 40 %	
Spirits of Turpentine	—	008006-64-2	—	Xn	X	2/2	3/4	1/0	4/4	1/0	3/3																				

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT						
						HDPE	LDPE	PA	PC	PETG	PMMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	PEP	PTFE	PVDF	EPDM	FKM		NBR	SI	AL	V2A	V4A	
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/0	1/1	1/0	1/0		
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Sugar beet juice	—	—	—	—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Sugar syrup	—	—	—	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Sulfur	S ₈	007704-34-9	techn. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	flower of sulfur	
Sulfur (mono)chloride	S ₂ Cl ₂	010025-67-9	—	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/1	1/0	4/4	1/0	4/4	0/0	3/4	1/1L	1/1L			
Sulfur dioxide	SO ₂	007446-09-5	damp	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	with H ₂ O->sulfurous acid	
Sulfur dioxide	SO ₂	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	with H ₂ O->sulfurous acid	
Sulfur hexafluoride	SF ₆	002551-62-4	—	—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Sulfur trioxide	SO ₃	007446-11-9	—	C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)		
Sulfur, melted, 121 °C	S ₈	007704-34-9	?	?		0	0	(4)	(3)	0	4	4	4	0	4	0	0	0	0	0	(1)	0	4	4	0	4	0	(3)	1	1	
Sulfuric acid	H ₂ SO ₄	007664-93-3	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3			
Sulfuric acid	H ₂ SO ₄	007664-93-3	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4		
Sulfuric acid	H ₂ SO ₄	007664-93-3	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3		
Sulfuric acid	H ₂ SO ₄	007664-93-3	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3		
Sulfuric acid	H ₂ SO ₄	007664-93-3	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	oleum		
Sulfuric acid	H ₂ SO ₄	007664-93-3	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2		
Sulfuric acid	H ₂ SO ₄	007664-93-3	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Sulfuric acid	-> see: Battery acid																														
Sulfurous acid	H ₂ SO ₃	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1		
Sulfurous acid, disodium salt	-> see: Sodium sulfite																														
Sulfuryl chloride	Cl ₂ SO ₂	007791-25-5	techn. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Tallow	—	—	techn. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Tannic acid	C ₇₆ H ₅₂ O ₄₈	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1		
Tannic acid	C ₇₆ H ₅₂ O ₄₈	001401-55-4	—	Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	1/1	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1		
Tanning extracts	—	—	?	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1		
Tanning extracts, vegetable	—	—	techn. usually	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1		
Tar	—	—	—	T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)		
Tartaric acid	C ₄ H ₆ O ₆	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2		
Tartaric acid	C ₄ H ₆ O ₆	000087-69-4	—	Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2			
Tetrabromoethane (TBE)	C ₂ H ₂ Br ₄	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	isomer not indicated in the source	
Tetrachlorethane	C ₂ H ₂ Cl ₄	—	techn. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	0/0	(3)	0/0	0/0	0/0	0/0	isomer not indicated in the source	
Tetrachlorodifluoroethane	C ₂ Cl ₂ F ₂	000076-12-0	?	?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0			
Tetrachloroethylene	C ₂ Cl ₄	000127-18-4	—	Xn		4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	4/4	2/3	4/4	0/0	(3)	0/0	0/0	Perchloroethylene; Tetrachloroethene	
Tetrahydrofuran (THF)	C ₄ H ₈ O	000109-99-9	—	F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Tetrahydrofurfuryl alcohol	C ₅ H ₁₀ O ₂	000097-99-4	—	Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(4)	0/0	(2)	(1)	(1)			
Tetrahydronaphthalene	C ₁₀ H ₁₂	000119-64-2	techn. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1			
Thiocyanic acid, ammonium salt	-> see: Ammonium thiocyanate																														
Thioglycolic acid	C ₂ H ₃ SO ₂	000068-11-1	—	T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1		
Thionyl chloride	Cl ₂ SO	007719-09-7	techn. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Thiophene	C ₄ H ₄ S	000110-02-1	—	F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)		
Thymol	C ₁₀ H ₁₄ O	000089-83-8	—	C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	3/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanium (tetra)chloride	TiCl ₄	007550-45-0	—	C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluene	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1		
Train oil	—	—	—	—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Transformer oil	—	—	—	?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/0	1/0	1/0	1/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)		
Triacetin	C ₉ H ₁₄ O ₆	000102-76-1	—	Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribromomethane	CHBr ₃	000075-25-2	—	T		4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0		
Tributyl citrate (TBC)	C ₁₈ H ₃₂ O ₇	000077-94-1	—	—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	0/0	(1)	(1)	(1			

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics			elastomers		metals		COMMENT								
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SA	ECTE / ETFE	FEP	PTFE	PVDF	EPDM	FKM	NBR		SI	AL	V2A	V4A				
Triethylene glycol diacetate	C ₁₆ H ₁₈ O ₆	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	
Trihydroxypropane, 1,2,3-	-> see: Glycerol																																	
Triiodomethane	-> see: Iodoform																																	
Triisopropylbenzene	C ₁₅ H ₂₄	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Trimethylbenzene, 1,2,4-	C ₉ H ₁₂	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1			
Trimethylolpropane	C ₆ H ₁₄ O ₃	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)				
Trimethylpentane, 2,2,4-	C ₈ H ₁₈	000540-84-1	techn. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	1/1				
Trioctyl phosphate	C ₂₄ H ₅₄ PO ₄	000078-42-2	techn. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	(2)	1/3	0/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)					
Tripropylene glycol (TPG)	C ₉ H ₂₀ O ₄	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	(2)	(3)	(2)	(3)	(2)	(3)	0/0	(1)	(1)					
Trisodium phosphate	Na ₃ PO ₄	007601-54-9		Xi		1/1	1/1	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1						
Turbine oil (based on mineral oil)	?																																	
Turpentine surrogate	—																																	
Two-stroke oil	100 %																																	
Undecanol	C ₁₁ H ₂₄ O	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)						
Urea	CH ₄ N ₂ O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1			
Urea	CH ₄ N ₂ O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/0	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/0	1/1	1/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1			
Uric acid	C ₅ H ₄ N ₄ O ₃	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1							
Urine	—																																	
Urotropin	-> see: Hexamethylenetetramine																																	
Valerian drops	?																																	
Vaseline	080009-03-8 techn. pure (—)																																	
Vaseline oil	080012-95-1 100 % ?																																	
Vaseline oil	080012-95-1 ?																																	
Vegetable oils	—																																	
Vinegar	C ₂ H ₄ O ₂	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2						
Vinyl acetate	C ₄ H ₈ O ₂	000108-05-4	techn. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)	1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/0	1/0	3/0	3/3	0/0	(1)	(1)							
Vinyl carbinol	-> see: Allyl alcohol																																	
Vinyl chloride (VCM)	C ₂ H ₃ Cl	000075-01-4	techn. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0	(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0						
Vinyl cyanide	-> see: Acrylonitrile																																	
Vinylidene chloride	C ₂ H ₂ Cl ₂	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0						
Vitamin C	C ₆ H ₈ O ₆	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)							
Walnut oil	080024-09-7																																	
Washingup liquid	aqueous ?																																	
Water	H ₂ O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1						
Water, distilled ~	H ₂ O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1						
Wax alcohol	080012-95-1 techn. pure (—)																																	
Waxes	080012-95-1																																	
Wetting agent	5 % ?																																	
Whey	1/1 0/0 (2) (1) (1) 0/0 (2) 1/1 0/0 0/0 0/0 0/0 0/0 1/1 1/1 1/1 (1) (3) (1) (2) 0/0 (2) 1/1 1/1																																	
Whiskey	080012-95-1																																	
White Spirit	080042-47-5																																	
Wines	—																																	
Wort for fermentation	?																																	
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1							
Xylene	C ₈ H ₁₀	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1							
Yeast	1/1 1/1 1/0 (1) 1/0 0/0 1/1 1/0 0/0 1/0 1/0 0/0 1/1 1/1 1/1 1/0 1/0 1/1 1/1 1/1 1/1 1/0 1/0 1/0 1/1 (1) (1)																																	
Zinc acetate	C ₄ H ₂ ZnO ₄	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)							
Zinc bromide	ZnBr ₂	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0							
Zinc carbonate	ZnCO ₃	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)							
Zinc chloride	ZnCl ₂	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/1	1/1	1/1	0/0	3/4	1/4L	1/3L						
Zinc nitrate	Zn(NO ₃) ₂	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	0/0	1/0	1/0	1/0	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)							
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1						
Zinc oxide ointment	?																																	
Zinc phosphate	Zn ₃ (PO ₄) ₂	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)							
Zinc sludge	?																																	
Zinc stearate	C ₃₆ H ₇₀ ZnO ₄	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)								
Zinc sulfate	ZnSO ₄	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1						
Zinkchlorid	ZnCl ₂	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L						

Chemical resistance

Two values are given per substance: left number = value at +20°C / right number = value at +50°C.

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATI ON	HAZARD NOTE	thermoplastics														fluoroplastics			elastomers			metals		COMMENT
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM	NBR	SI	

0	no data available
1	resistant
2	practically resistant
3	partially resistant
4	not resistant
K	no general information available
L	danger of pitting or stress-cracking corrosion
()	estimated value

Hazard notes

E	explosive
O	oxidizing
F	highly flammable
F+	extremely flammable
T	toxic
T+	very toxic
C	corrosive
Xn	harmful
Xi	irritant
N	dangerous for the environment

Description of the materials

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Hala®)
ETFE	Ethylene-tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon® FEP)
PTFE	Polytetrafluoroethylene (Teflon®)
PVDF	Polyvinylidene fluoride